



TECHNICAL DATA

POWDER JK7109

Trade name: Powder JK7109 WC10Co4Cr - 45/15µm


POWDER JK7109 WC10CO4CR - 45/15µM

	W	Co	Cr	C (Total)	C (Free)	O	Fe	Other Elements
%Typical Value	Balance	10,0	4,0	5,4	0,03	0,05	0,03	< 0,5

PHYSICAL PROPERTIES

Physical properties	Flow Rate(s/50g)	Apparent Density(g/cm ³)	Apparent Density(g/cm ³)
Typical Value	>= 380 mm	420 mm	420 mm

Stellite™, Tribaloy™, Nistelle™, Stelcar™, Jet Kote™, and Delcrome™ are registered trademarks of Kennametal Inc.



Deloro Wear Solutions GmbH manufactures and markets sophisticated alloys in the form of castings, powders, coatings, consumables, and machined parts that resist wear, corrosion, and abrasion. Information provided in this document is intended only for general guidance about Deloro Wear Solutions™ products and is the best information in our possession at the time. Product users may request information about their individual use of our products, but Deloro Wear Solutions™ does not warrant or guarantee this information in any way. Selection and purchase of Deloro Wear Solutions™ products is the sole responsibility of the product user based on the suitability of each use. Individual applications must be fully evaluated by the user, including compliance with applicable laws, regulations, and non-infringement. Deloro Wear Solutions™ cannot know or anticipate the many variables that affect individual product use and individual performance results may vary. For these reasons, Deloro Wear Solutions™ does not warrant or guarantee advice or information in this document, assumes no liability regarding the same, and expressly disclaims any warranty of any kind, including any warranty of fitness for a particular purpose, regarding the same.